

RL-TR-96-201
Final Technical Report
December 1996



SATURABLE ABSORBING QUANTUM WELLS AT 1.55 MICRON

Gary W. Wicks, Consultant

19970211 022

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED.


[DTIC QUALITY INSPECTED 3]

Rome Laboratory
Air Force Materiel Command
Rome, New York

This report has been reviewed by the Rome Laboratory Public Affairs Office (PA) and is releasable to the National Technical Information Service (NTIS). At NTIS it will be releasable to the general public, including foreign nations.

RL-TR-96-201 has been reviewed and is approved for publication.

APPROVED: 
REINHARD K. ERDMANN
Project Engineer

FOR THE COMMANDER: 
DONALD W. HANSON, Director
Surveillance & Photonics Directorate

If your address has changed or if you wish to be removed from the Rome Laboratory mailing list, or if the addressee is no longer employed by your organization, please notify RL/OCPA, 25 Electronic Pky, Rome, NY 13441-4514. This will assist us in maintaining a current mailing list.

Do not return copies of this report unless contractual obligations or notices on a specific document require that it be returned.

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE December 1996	3. REPORT TYPE AND DATES COVERED FINAL, May 95 - May 96	
4. TITLE AND SUBTITLE SATURABLE ABSORBING QUANTUM WELLS AT 1.55 MICRON			5. FUNDING NUMBERS C - F30602-95-C-0069 PE - 62702F PR - 4600 TA - P4 WU - PN	
6. AUTHOR(S) Gary W. Wicks				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Gary W. Wicks, Consultant 49 Courtenay Circle Pittsford NY 14534			8. PERFORMING ORGANIZATION REPORT NUMBER N/A	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) Rome Laboratory/OCPA 25 Electronic Pky Rome NY 13441-4514			10. SPONSORING / MONITORING AGENCY REPORT NUMBER RL-TR-96-201	
11. SUPPLEMENTARY NOTES Rome Laboratory Project Engineer: Reinhard K. Erdmann, OCPA, (315) 330-4455				
12a. DISTRIBUTION AVAILABILITY STATEMENT APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) Multiple Quantum Well structures are grown on indium phosphide substrates by molecular beam epitaxy (MBE). These are designed to generate photoluminescence and a saturable absorbing edge at 1.55 um. Samples of various concentrations are grown and spectrally characterized. Suitability as an erbium fiber laser modelocked is being tested at Rome Lab.				
14. SUBJECT TERMS saturable absorbers, fiber lasers, multiple quantum wells, modelocked lasers			15. NUMBER OF PAGES 20	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UNLIMITED	

NSN 7540-01-280-5500

Standard Form 298 (Rev. 2-89)
Prescribed by ANSI Std. Z39-18
298-102

DTIC QUALITY INSPECTED 3

Table of Contents

INTRODUCTION	1
DESCRIPTION OF SAMPLES	1
CW LINEAR OPTICAL SPECTRA OF SAMPLES	2
Transmission spectra	2
Photoluminescence	2
DISCUSSION OF DATA	9
CONCLUSIONS	9

Introduction

Saturable absorbers constructed of semiconductor quantum wells have been successfully employed in mode locking Ti:sapphire lasers. In these applications, the saturable absorbing quantum well sample is positioned inside the laser cavity and passively, *i.e.* without electrical or optical control, causes the laser to mode lock. It was the aim of this project to develop semiconductor quantum wells suitable for mode locking Er^{3+} fiber lasers.

Ti:sapphire lasers operate in the $\lambda \sim 800$ nm range. The appropriate semiconductor material system for saturable absorption at 800 nm is AlGaAs/GaAs. The present application requires saturable absorption at $\lambda \sim 1.55$ μm , which necessitates a different choice of semiconductor materials. There are two reasonably well developed semiconductor material systems for construction of quantum wells with near band edge (saturable) absorption at 1.55 μm , $\text{Al}_{0.48}\text{In}_{0.52}\text{As}/\text{Ga}_{0.47}\text{In}_{0.53}\text{As}$ and $\text{InP}/\text{Ga}_{0.47}\text{In}_{0.53}\text{As}$. The molecular beam epitaxy (MBE) system used for the growth of the semiconductor samples for this project has the capability of growing both of these 1.55 μm material systems. The former system is easier to grow since it contains only a single group V element, arsenic; it will be emphasized in the proposed task. The latter material system requires the use of two group V elements, arsenic and phosphorus. If necessary this second material system can be employed.

The primary aim of this project was the growth and evaluation of $\text{Al}_{0.48}\text{In}_{0.52}\text{As}/\text{Ga}_{0.47}\text{In}_{0.53}\text{As}$ quantum well structures for mode locking of Er^{3+} fiber lasers. The effect of MBE growth conditions on the performance of the mode locking ability of the samples was investigated. The low intensity absorption spectra of the samples were measured. After measurement of their cw, linear optical properties samples were delivered to K. Teegarden / R. Erdmann of Rome Labs for mode locking evaluation in an Er^{3+} fiber laser. Additionally, quantum wells consisting of the backup material system, $\text{InP}/\text{Ga}_{0.47}\text{In}_{0.53}\text{As}$, were constructed and evaluated.

Description of Samples

During the course of this project, a total of 9 samples were grown by molecular beam epitaxy (MBE). All samples consisted of a 50 periods of 100 Å wells and 100 Å barrier layers deposited on InP substrates. The total thickness of the the layers ($50 \times [100\text{Å} + 100\text{Å}]$) is 1 μm ; the nominal substrate thickness is 500 μm .

In all cases the well material is $\text{Ga}_{0.47}\text{In}_{0.53}\text{As}$. Most of the samples had InP barriers, but two had $\text{Al}_{0.48}\text{In}_{0.52}\text{As}$ barriers.

The samples are summarized in table 1.

sample no.	structure	growth temperature (°C)	absorption edge wavelength (nm)	exciton structure	comments
1298	AlInAs/GaInAs	490	-		unsuccessful growth
1303	AlInAs/GaInAs	490	-		
1305	AlInAs/GaInAs	490	1620	none	grown like 1303, except with higher arsenic flux
1442	InP/GaInAs	430			
1444	InP/GaInAs	430	~1590	very weak	grown like 1442, except shorter phosphorus growth stop
1461	AlInAs/GaInAs	430	1607	none	
1544	AlInAs/GaInAs	520	1645	strong	
1580	AlInAs/GaInAs	445	1624	strong	
1590	AlInAs/GaInAs	405	1617	moderate	grown like 1580, except lower growth temperature

Table 1. Summary of growth parameters and optical transmission spectral characteristics of samples grown for the this project.

CW Linear Optical Spectra of Samples

Transmission spectra

The cw linear optical transmission spectrum of six of the samples were measured with a commercial spectrophotometer. The absorption edge was estimated by visual inspection of the data, and is listed in table 1. Also listed in table is the qualitative strength of the exciton features in the transmission spectra. These six transmission spectra are shown in figures 1 - 6.

Photoluminescence

Room temperature photoluminescence was measured on two of the samples, numbers 1442 and 1444. These two spectra are shown in figure 7.

The spectral dependence of the photoluminescence of #1442 and #1444 are very similar. It is very likely that the absorption edges of the two samples are therefore also very similar.

Thus, although no transmission spectrum was measured on #1442, it is reasonable to assume that the absorption edge of #1442 is also around 1590 nm.

The two spectra were not measured under identical conditions. The spectrometer slits were different for the two measurements, producing different spectrometer throughput. Taking the difference in spectrometer throughput into account, sample #1442 has more intense photoluminescence than #1444 by a factor of 2.25.




Figure 1. Transmissivity (arb. units) vs. Wavelength (nm) for sample #1305.




Figure 2. Transmissivity (arb. units) vs. Wavelength (nm) for sample #1444.




Figure 3. Transmissivity (arb. units) vs. Wavelength (nm) for sample #1461.




Figure 4. Transmissivity (arb. units) vs. Wavelength (nm) for sample #1544.




Figure 5. Transmissivity (arb. units) vs. Wavelength (nm) for sample #1508.




Figure 6. Transmissivity (arb. units) vs. Wavelength (nm) for sample #1590.




Figure 7. Photoluminescence Spectra of samples #1442 and #1444.

Discussion of data

This project concentrated on investigating two main sample parameters that would affect the use of these samples for mode locking fiber lasers. The first parameter is the wavelength of the absorption edge. The absorption edge, and essentially the entire absorption spectrum, can be shifted in wavelength by adjusting through the quantum well thicknesses and compositions. As the absorption edge is moved to longer and longer wavelengths beyond the lasing wavelength, the sample's linear absorption at the lasing wavelength becomes stronger and, presumably, the saturation intensity of the sample becomes larger.

A second characteristic of the sample which is important in saturable absorbing applications, is the carrier lifetime. Presumably, as the carrier lifetime becomes shorter, the saturation intensity of the sample increases. The carrier lifetime in these samples is probably dominated by non-radiative recombination. The density of non-radiative recombination centers is affected by the several different parameters of the MBE growth, growth temperature being the primary parameter. This density of non-radiative recombination centers is difficult to measure directly, but can be qualitatively indicated by the strength of exciton features in the transmission spectrum and by photoluminescence intensity. Both of these types of measurements were performed in this project, with emphasis placed on the exciton absorption. It was found that the strength of the exciton absorption decreased, and presumably the saturation intensity increased, as the MBE growth temperature decreased.

The main activity of the project is the construction of quantum well samples that absorb at $1.55\text{ }\mu\text{m}$, and the investigation of how the linear absorption properties can be affected by the way in which the MBE growth is carried out. A suggested second stage of this topic would be an investigation of how the non-linear (saturable) absorption is affected by the way in which the MBE growth is carried out. Apparently some of these non-linear measurements are already under way at Rome Laboratory.

Conclusions

It has been demonstrated in this project that quantum well structures with saturable absorption near $1.55\text{ }\mu\text{m}$ can be grown by MBE. The MBE growth conditions used to produce the quantum well sample have significant effects on the linear and nonlinear optical properties of the samples. Optimization of the MBE growth to produce the best mode locking behavior was begun in this project.

A potentially useful direction for future research in this area is the construction of electrically controlled saturable absorbers for active, rather than passive, mode locking. Such structures might be useful to reduce jitter in mode locking repetition rates.

MISSION OF ROME LABORATORY

Mission. The mission of Rome Laboratory is to advance the science and technologies of command, control, communications and intelligence and to transition them into systems to meet customer needs. To achieve this, Rome Lab:

- a. Conducts vigorous research, development and test programs in all applicable technologies;
- b. Transitions technology to current and future systems to improve operational capability, readiness, and supportability;
- c. Provides a full range of technical support to Air Force Material Command product centers and other Air Force organizations;
- d. Promotes transfer of technology to the private sector;
- e. Maintains leading edge technological expertise in the areas of surveillance, communications, command and control, intelligence, reliability science, electro-magnetic technology, photonics, signal processing, and computational science.

The thrust areas of technical competence include: Surveillance, Communications, Command and Control, Intelligence, Signal Processing, Computer Science and Technology, Electromagnetic Technology, Photonics and Reliability Sciences.